

**DESCRIPTION:**

Tacusil UVA0219LVT maskant can cure with UV/Visible light and is designed for temporary protection for component and connector in SMT and SMT post-procedure. It's the lower viscosity version of Tacusil UVA 0219 maskant with good water and chemical resistance. This maskant don't contain solvent and cure fast enable to improve production efficiency. It also has good protection and can be easily peeled off without residue.

Because of oxygen inhibition on its surface during curing process, short wave length UV light as 260nm will reduce its surface tacky. This product is Halogen free and full complaint with RoHS directive 2011/65/EU and Reach directive 1907/2006(SVHC: 201 Items)

**TYPICAL PROPERTIES:**

All properties given are at 25 °C unless otherwise noted.

<b>Property:</b>	<b>Value:</b>	<b>Test Method or Source:</b>
<b>Color</b>	Translucence	Visual
<b>Cure Schedule</b>		
<b>The minimum UV light intensity</b>	200Mw/mm2	455300005390 / Power Puck II
<b>Typical Curing time(0.5mm thickness)</b>	20s	Radiometer
<b>Viscosity</b>	13000cps @1/s	Rheometer parallel plate 25mm@1/s
<b>Thixotrophy area</b>	2000Pa.s	455300006291
<b>Specific Gravity</b>	1.1	Calculated
<b>Hardness</b>	55A	455300006287/ASTM D2240
<b>Water Absorption</b>	0.8% after 24 hours	457561824543/ASTM D570
<b>Tensile Properties:</b>		
<b>Strength</b>	3.8Mpa(550psi)	455300006285/ASTM D638/MTS
<b>Elongation(speed:50mm/min)</b>	580%	4535601224470/ASTM D638/Instron
<b>Non volatile content</b>	100	455300005646
<b>Coefficient of Thermal Expansion by TMA</b>	220ppm	455300005340/ASTM E831 TMA, 5 °C/min
<b>Service temperature *</b>	-40~120C	
<b>Linear Shrinkage*</b>	2%	ASTM2556

\* Asterisk denotes values considered typical to associated resin systems or extrapolated from other test results.

\*\* This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology.

**INSTRUCTIONS:**

1 This product cured with exposure to UV and visible light. Dispensing components including needles and fluid lines should be 100% light locking not just UV blocking.

2 For best performance bond surfaces should be clean and free from grease. Good exhaustion is necessary in the curing circumstance.

TACUSIL MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE with respect to its products. In addition, while the information contained herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestions for use are made without guarantee inasmuch as conditions of use are beyond our control. The properties given are typical values and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.



# TECHNICAL DATA SHEET Tacusil UVA0219LVT

3/10/2020

3 Cure speed is dependent upon many variables including lamp intensity, adhesive thickness and percent light transmission of components.

4 Oxygen in the atmosphere may inhibit surface cure. UVC light and high inert gas content in curing ambient will help to eliminate this surface tacky.

5 Heat under UV light will warm the assembled parts, peeled it off after cooling down.

## **SHELF LIFE AND STORAGE:**

Store product in the unopened container in a dry location.

Storage information may be indicated on the product container labeling.

**Optimal Storage: 10 °C to 32 °C.**

Material removed from containers may be contaminated during use. Do not return product to the original container. KPHZ cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated.

## **NOTES:**

This product is intended for industrial use only. Keep it way from children. Personal protection wearing in necessary in using this adhesive including gloves, glass and face mask. In case contact it, remove it with soap and water. Make sure the operator to know clearly its safety information in SDS before use.